



BOARDWALK

THE NAME SAYS IT ALL. BOARDWALK IS A RUSTIC TEXTURED WOODGRAIN WITH A DEEP BROWN WEATHERED FEEL. IT IS PARTICULARLY APPLICABLE FOR USE IN A HORIZONTAL FORMAT SUCH AS A TRAY OR TABLETOP. FALL IN LOVE WITH THE LOOK, BUT WITHOUT THE SPLINTERS.

BOARDWALK IS OFFERED IN A HEAVILY TEXTURED FINISH AND IS SUITABLE FOR VERTICAL AND HORIZONTAL APPLICATIONS. IT IS EASY TO CLEAN, DOESN'T CHIP, IS HIGHLY DURABLE AND HAS LONG TERM UV STABILITY.

COMPLEMENTARY MATERIALS
[CLICK HERE](#)

PENTADECOR® 3D LAMINATE
COLOR CODE: WE/0201
PARALLEL ✓





BOARDWALK

PENTADECOR® 3D LAMINATE

STOCK RANGE ✓ PARALLEL ✓

COLOR CODE: WE/0201 EMBOSSING: H56 ML TOPCOAT: MATTE LINE (ML)

PERFORMANCE SUMMARY

- BLEACH SOLUTION CLEANABLE
- EXCELLENT SOIL & STAIN RESISTANCE
- NATURAL FLUID BARRIER
- EXCELLENT ABRASION & IMPACT RESISTANCE
- EXCELLENT COLOR STABILITY

ENVIRONMENTAL

- NO ADDED FLAME RETARDANTS
- NO ADDED ANTIMICROBIALS
- DOES NOT CONTAIN FORMALDEHYDE
- FORMULATED WITHOUT PHTHALATES

CLEANING AND MAINTENANCE

- WATER AND MILD LIQUID SOAP CLEANABLE

ITEM SPECIFICATIONS

MOQ : NONE

SURFACE TEXTURE/EMBOSSING : LINEAR PEAKS AND VALLEYS / HEAVY **SURFACE GLOSS** : LEVEL 6 **SURFACE FINISH LACQUER** : SCRATCH & STAIN RESISTANT POLYURETHANE **GAUGE** : .014" (350MY) **WIDTH** : 57" (1450MM) **ROLL SIZE** : 250 LM/ROLL **DESIGN REPEAT (RAPPORT)** : N/A

SUITABLE FOR : MEMBRANE PRESSING – FLAT LAMINATION – PROFILE WRAPPING – MITER FOLDING

PERFORMANCE CHARACTERISTICS

3.8 BALL IMPACT NEMA* : >3000MM (118")

3.9 IMPACT RESISTANCE NEMA* : >1000MM (39")

3.13 WEAR RESISTANCE NEMA* : 750 CYCLES

3.4 CLEANABILITY & STAIN RESISTANCE NEMA* : 14

LIGHT FASTNESS ISO 105-BO2 WBS : 6-7

LIGHT REFLECTIVE VALUE (LRV) : N/A

FLUID BARRIER : INHERENT FLUID BARRIER (NATURALLY HYDROPHOBIC)

MEDICAL REAGENTS : COMPATIBLE WITH COMMON CLEANERS, REAGENTS AND DISINFECTANTS USED IN N.A.

ASTM E84 : CLASS A

REDUCED ENVIRONMENTAL IMPACT: MANUFACTURED WITHOUT PLASTICIZERS, PHTHALATES, OR HEAVY METALS

Test results may vary by color and design

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be understood as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed.



COMPLEMENTARY MATERIALS
CLICK HERE