



**COMPLEMENTARY MATERIALS**  
[CLICK HERE](#)



## SIENA SM

DON'T BE AFRAID TO USE MORE THAN ONE DARKER COLOR IN A ROOM DESIGN. PLAYING WITH GLOSS LEVELS CAN CREATE INTERESTING EFFECTS, AND IT ALLOWS LIGHTER COLORS TO PLAY ACCENT FOR A CHANGE. SIENA IS A PERFECT TONE TO ACHIEVE THIS EFFECT.

SSI'S SUPER MATTE FINISH HAS THE LOOK AND FEEL OF A HIGH QUALITY PAINTED FINISH, BUT WITH SUPERIOR PERFORMANCE. IT IS EASY TO CLEAN, DOESN'T CHIP. IS HIGHLY DURABLE AND HAS LONG TERM UV COLOR STABILITY.

**PENTADECOR® 2D LAMINATE**  
**COLOR CODE: 75/4203**





# SIENA SM

## PENTADECOR® 2D LAMINATE

STOCK RANGE ✓

COLOR CODE: 75/4203 EMBOSSING: A13 ML TOPCOAT: SENDURA

### PERFORMANCE SUMMARY

- BLEACH SOLUTION CLEANABLE
- EXCELLENT SOIL & STAIN RESISTANCE
- NATURAL FLUID BARRIER
- EXCELLENT ABRASION & IMPACT RESISTANCE
- EXCELLENT COLOR STABILITY

### ENVIRONMENTAL

- NO ADDED FLAME RETARDANTS
- NO ADDED ANTIMICROBIALS
- DOES NOT CONTAIN FORMALDEHYDE
- FORMULATED WITHOUT PHTHALATES

### CLEANING AND MAINTENANCE

·WATER AND MILD LIQUID SOAP CLEANABLE

### ITEM SPECIFICATIONS

MOQ : NONE

SURFACE TEXTURE/EMBOSSING : SMOOTH SURFACE

SURFACE GLOSS : LEVEL 4

SURFACE FINISH LACQUER : SCRATCH, STAIN, FINGERPRINT RESISTANT SENDURA TC

GAUGE : .008" (200MY) WIDTH : 49.2" (1250MM)

ROLL SIZE : 500 LM/ROLL DESIGN REPEAT (RAPPORT) : SOLID COLOR∞

SUITABLE FOR : FLAT LAMINATION – PROFILE

WRAPPING – MITER FOLDING

### PERFORMANCE CHARACTERISTICS

TENSILE STRENGTH (MD) : N/MM2 - >40

LIGHT FASTNESS : WBS - 6-7

CHEMICAL RESISTANCE : CLASS - 1B

SCRATCH RESISTANCE (ERICHSEN) : 4E

SCRATCH RESISTANCE MARTINDALE A : 25

RESISTANCE TO DRY HEAT : 7C (100 C)

RESISTANCE TO WET HEAT : 8B (70 C)

FLUID BARRIER : INHERENT FLUID BARRIER (NATURALLY HYDROPHOBIC)

MEDICAL REAGENTS : COMPATIBLE WITH COMMON CLEANERS, REAGENTS AND DISINFECTANTS USED IN N.A.

ASTM E84 : CLASS A

REDUCED ENVIRONMENTAL IMPACT: MANUFACTURED WITHOUT PLASTICIZERS, PHTHALATES, OR HEAVY METALS

### COMPLEMENTARY MATERIALS

[CLICK HERE](#)

\*Test results may vary by color and design

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be understood as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed.