



COMPLEMENTARY MATERIALS
[CLICK HERE](#)

WHITE SM

WHITE SUPER MATTE IS A WARM WHITE STAPLE WITH A CLASSIC MATTE PAINT-LIKE FINISH. THIS COLOR IS DESIGNED TO BE USED AS A STAND-ALONE STAR OR TO BE THE PERFECT PARTNER WHEN COMBINED WITH OTHER SOLIDS OR WOODGRAIN DESIGNS IN MULTIPLE APPLICATIONS.

SSI'S SUPER MATTE FINISH HAS THE LOOK AND FEEL OF A HIGH QUALITY PAINTED FINISH, BUT WITH SUPERIOR PERFORMANCE. IT IS EASY TO CLEAN, DOESN'T CHIP, IS HIGHLY DURABLE AND HAS LONG TERM UV COLOR STABILITY.

PENTADecOR® 2D LAMINATE
COLOR CODE: 04/2090





WHITE SM

PENTADECOR® 2D LAMINATE

STOCK RANGE ✓

COLOR CODE: 04/2090 EMBOSSING: A13 ML TOPCOAT: SENDURA

PERFORMANCE SUMMARY

- BLEACH SOLUTION CLEANABLE
- EXCELLENT SOIL & STAIN RESISTANCE
- NATURAL FLUID BARRIER
- EXCELLENT ABRASION & IMPACT RESISTANCE
- EXCELLENT COLOR STABILITY

ENVIRONMENTAL

- NO ADDED FLAME RETARDANTS
- NO ADDED ANTIMICROBIALS
- DOES NOT CONTAIN FORMALDEHYDE
- FORMULATED WITHOUT PHTHALATES

CLEANING AND MAINTENANCE

·WATER AND MILD LIQUID SOAP CLEANABLE

ITEM SPECIFICATIONS

MOQ : NONE SURFACE TEXTURE/EMBOSSING : SMOOTH SURFACE SURFACE GLOSS : LEVEL 4 SURFACE FINISH LACQUER : SCRATCH, STAIN,

FINGERPRINT RESISTANT SENDURA TC

GAUGE : .008" (200MY) WIDTH : 49.2" (1250MM)

ROLL SIZE : 500 LM/ROLL DESIGN REPEAT (RAPPORT) : SOLID COLOR∞

SUITABLE FOR : FLAT LAMINATION – PROFILE

WRAPPING – MITER FOLDING

PERFORMANCE CHARACTERISTICS

TENSILE STRENGTH (MD) : N/MM2 - >40

LIGHT FASTNESS : WBS - 6-7

CHEMICAL RESISTANCE : CLASS - 1B

SCRATCH RESISTANCE (ERICHSEN) : 4E

SCRATCH RESISTANCE MARTINDALE A : 25

RESISTANCE TO DRY HEAT : 7C (100 C)

RESISTANCE TO WET HEAT : 8B (70 C)

FLUID BARRIER : INHERENT FLUID BARRIER (NATURALLY HYDROPHOBIC)

MEDICAL REAGENTS : COMPATIBLE WITH COMMON CLEANERS, REAGENTS AND DISINFECTANTS USED IN N.A.

ASTM E84 : CLASS A

REDUCED ENVIRONMENTAL IMPACT: MANUFACTURED WITHOUT PLASTICIZERS, PHTHALATES, OR HEAVY METALS

COMPLEMENTARY MATERIALS

[CLICK HERE](#)

*Test results may vary by color and design

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be understood as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed.