


COMPLEMENTARY MATERIALS

[CLICK HERE](#)



CANADIAN GREY SM

CANADIAN GREY SM IS A WARM MID-TONE GREY WITH A VERY SUBTLE RED UNDERTONE WITH A PERFECT SUPER MATTE SURFACE FINISH. GREAT FOR COMMERCIAL SPACES, PAIRS WELL WITH OTHER DARK SOLIDS AND WOODGRAINS.

CANADIAN GREY SM IS OFFERED IN A MATTE VELVET FINISH WITH A GLOSS LEVEL OF 4-6, AND IS SUITABLE FOR VERTICAL AND LIGHT HORIZONTAL APPLICATIONS. IT IS EASY TO CLEAN, DOESN'T CHIP, IS HIGHLY DURABLE AND HAS LONG-TERM UV STABILITY.

PENTADECOR® 3D LAMINATE
COLOR CODE: 75/6804
PARALLEL  





CANADIAN GREY SM

PENTADECOR® 3D LAMINATE

STOCK RANGE ✓ PARALLEL ✗

COLOR CODE: 75/6804 EMBOSSING: A16 ML TOPCOAT: MATTE LINE (ML)

PERFORMANCE SUMMARY

- BLEACH SOLUTION CLEANABLE
- EXCELLENT SOIL & STAIN RESISTANCE
- NATURAL FLUID BARRIER
- EXCELLENT ABRASION & IMPACT RESISTANCE
- EXCELLENT COLOR STABILITY

ENVIRONMENTAL

- NO ADDED FLAME RETARDANTS
- NO ADDED ANTIMICROBIALS
- DOES NOT CONTAIN FORMALDEHYDE
- FORMULATED WITHOUT PHTHALATES

CLEANING AND MAINTENANCE

• WATER AND MILD LIQUID SOAP CLEANABLE

ITEM SPECIFICATIONS

MOQ : NONE SURFACE TEXTURE/EMBOSSING :
SMOOTH SURFACE SURFACE GLOSS : LEVEL 6
SURFACE FINISH LACQUER : SCRATCH & STAIN
RESISTANT POLYURETHANE GAUGE : .012" (300MY)
WIDTH : 57" (1450MM) ROLL SIZE : 250 LM/ROLL
DESIGN REPEAT (RAPPORT) : SOLID COLOR ∞

SUITABLE FOR : MEMBRANE PRESSING - FLAT

LAMINATION - PROFILE WRAPPING - MITER FOLDING

PERFORMANCE CHARACTERISTICS

3.8 BALL IMPACT NEMA* : >3000MM (118")
3.9 IMPACT RESISTANCE NEMA* : >1000MM (39")
3.13 WEAR RESISTANCE NEMA* : 3250 CYCLES
3.4 CLEANABILITY & STAIN RESISTANCE NEMA* : 14
LIGHT FASTNESS ISO 105-BO2 WBS : 6-7
LIGHT REFLECTIVE VALUE (LRV) : 38.73
FLUID BARRIER : INHERENT FLUID BARRIER
(NATURALLY HYDROPHOBIC)
MEDICAL REAGENTS : COMPATIBLE WITH COMMON
CLEANERS, REAGENTS AND DISINFECTANTS USED IN
N.A.
ASTM E84 : CLASS A
REDUCED ENVIRONMENTAL IMPACT: MANUFACTURED
WITHOUT PLASTICIZERS, PHTHALATES, OR HEAVY
METALS

Test results may vary by color and design

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be understood as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed.

COMPLEMENTARY MATERIALS

[CLICK HERE](#)