





ALMOND

PENTADECOR® 3D LAMINATE

COLOR CODE: 15/8608

PARALLEL 🗸 😑

ALMOND IS A LIGHT BEIGE BROWN COLORATION THAT IS WARMING WITH AN OVERALL CLASSIC LOOK. GREAT STANDALONE COLORATION THAT CAN ALSO WORK WELL WITH WHITE COLORS AND WOODGRAINS WITH RED UNDERTONES.

ALMOND'S SOLID FINISH HAS A LIGHT TEXTURE AND A GLOSS LEVEL OF AROUND 12–15. THIS SURFACE IS SUITABLE FOR BOTH VERTICAL AND HORIZONTAL APPLICATIONS. IT IS EASY TO CLEAN, DOESN'T CHIP. IS HIGHLY DURABLE AND HAS LONG-TERM UV COLOR STABILITY.

COMPLEMENTARY MATERIALS CLICK HERE

SSI NORTH AMERICA



ALMOND PENTADECOR® 3D LAMINATE

STOCK RANGE 🗸 🛛 PARALLEL 🗸 🖨

COLOR CODE: 15/8608 EMBOSSING: C75 BL TOPCOAT: BASIC LINE (BL)

PERFORMANCE SUMMARY

- BLEACH SOLUTION CLEANABLE
- EXCELLENT SOIL & STAIN RESISTANCE
- · NATURAL FLUID BARRIER
- EXCELLENT ABRASION & IMPACT RESISTANCE
- \cdot EXCELLENT COLOR STABILITY

ENVIRONMENTAL

- · NO ADDED FLAME RETARDANTS
- \cdot NO ADDED ANTIMICROBIALS
- \cdot DOES NOT CONTAIN FORMALDEHYDE
- · FORMULATED WITHOUT PHTHALATES

CLEANING AND MAINTENANCE

 \cdot WATER AND MILD LIQUID SOAP CLEANABLE

ITEM SPECIFICATIONS

MOQ : NONE

SURFACE TEXTURE/EMBOSSING : STIPPLED, HEAVY SURFACE GLOSS : LEVEL 11 SURFACE FINISH LACQUER : SCRATCH & STAIN RESISTANT POLYURETHANE GAUGE : .012" (300MY) WIDTH : 57" (1450MM) ROLL SIZE : 250 LM/ROLL DESIGN REPEAT (RAPPORT) : SOLID COLOR ∞ SUITABLE FOR : MEMBRANE PRESSING - FLAT

LAMINATION - PROFILE WRAPPING - MITER FOLDING

PERFORMANCE CHARACTERISTICS

3.8 BALL IMPACT NEMA* : >3000MM (118") 3.9 IMPACT RESISTANCE NEMA* : >1000MM (39") 3.13 WEAR RESISTANCE NEMA* : 3250 CYCLES 3.4 CLEANABILITY & STAIN RESISTANCE NEMA* : 14 LIGHT FASTNESS ISO 105-BO2 WBS : 6-7 LIGHT REFLECTIVE VALUE (LRV) : N/A FLUID BARRIER : INHERENT FLUID BARRIER (NATURALLY HYDROPHOBIC) MEDICAL REAGENTS : COMPATIBLE WITH COMMON CLEANERS, REAGENTS AND DISINFECTANTS USED IN N.A.

ASTM E84 : CLASS A REDUCED ENVIRONMENTAL IMPACT: MANUFACTURED WITHOUT PLASTICIZERS, PHTHALATES, OR HEAVY METALS

Test results may vary by color and design

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be understood as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industral property rights must be observed.

COMPLEMENTARY MATERIALS CLICK HERE