









COMPLEMENTARY MATERIALS **CLICK HERE**



SCULPTED WENGE

SCULPTED WENGE IS DESIGNED AFTER AN EXOTIC AFRICAN WOOD TEXTURE THAT IS EXPRESSIVE WITH A STRAIGHT TO ROEY GRAIN. THE COLOR IS A RICH DARK BROWN TO BLACK WITH FINE, CLOSELY SPACED DARK VEINS. BEST UTILIZED IN UPSCALE KITCHEN DESIGN, AND CRAFT MIXOLOGY BARS.

SCULPTED WENGE IS OFFERED IN A HEAVILY TEXTURED FINISH AND IS SUITABLE FOR VERTICAL AND HORIZONTAL APPLICATIONS. IT IS EASY TO CLEAN, DOESN'T CHIP, IS HIGHLY DURABLE AND HAS LONG-TERM UV STABILITY.

PENTADECOR® 3D LAMINATE COLOR CODE: LA/0103

PARALLEL 🗸 🛑





SCULPTED WENGE

PENTADECOR® 3D LAMINATE

STOCK RANGE V PARALLEL V =

COLOR CODE: LA/0103 EMBOSSING: H56 ML TOPCOAT: MATTE LINE (ML)

PERFORMANCE SUMMARY

- BLEACH SOLUTION CLEANABLE
- EXCELLENT SOIL & STAIN RESISTANCE
- NATURAL FLUID BARRIER
- EXCELLENT ABRASION & IMPACT RESISTANCE
- EXCELLENT COLOR STABILITY

ENVIRONMENTAL

- NO ADDED FLAME RETARDANTS
- NO ADDED ANTIMICROBIALS
- DOES NOT CONTAIN FORMALDEHYDE
- FORMULATED WITHOUT PHTHALATES

CLEANING AND MAINTENANCE

·WATER AND MILD LIQUID SOAP CLEANABLE



COMPLEMENTARY MATERIALS

CLICK HERE

ITEM SPECIFICATIONS

MOQ: NONE

SURFACE TEXTURE/EMBOSSING: LINEAR PEAKS AND VALLEYS / HEAVY SURFACE GLOSS: LEVEL 10 SURFACE FINISH LACQUER: SCRATCH & STAIN RESISTANT POLYURETHANE GAUGE: .014" (350MY) WIDTH: 57" (1450MM) ROLL SIZE: 250 LM/ROLL DESIGN REPEAT (RAPPORT): 1260MM / 49.606" SUITABLE FOR: MEMBRANE PRESSING - FLAT

LAMINATION - PROFILE WRAPPING - MITER FOLDING

PERFORMANCE CHARACTERISTICS

3.8 BALL IMPACT NEMA*: >3000MM (118")
3.9 IMPACT RESISTANCE NEMA*: >1000MM (39")
3.13 WEAR RESISTANCE NEMA*: 750 CYCLES

3.4 CLEANABILITY & STAIN RESISTANCE NEMA*: 14 LIGHT FASTNESS ISO 105-BO2 WBS: 6-7 LIGHT REFLECTIVE VALUE (LRV): N/A

FLUID BARRIER : INHERENT FLUID BARRIER (NATURALLY HYDROPHOBIC)

MEDICAL REAGENTS: COMPATIBLE WITH COMMON CLEANERS, REAGENTS AND DISINFECTANTS USED IN N.A.

ASTM E84 : CLASS A

REDUCED ENVIRONMENTAL IMPACT: MANUFACTURED WITHOUT PLASTICIZERS, PHTHALATES, OR HEAVY METALS

Test results may vary by color and design

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be understood as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industral property rights must be observed.